

# GARBA 188L

## Stainless spring wire

GARBA 188 is a general-purpose austenitic stainless steel, which is used for springs and other components requiring good fatigue resistance. GARBA 188L has a higher formability as compared to GARBA 188 due to its lower carbon content.

## Chemical composition

Element	Weight %
C	0.08%
Si	1.00%
Mn	2.00%
P max.	0.040%
S max.	0.015%
Cr	18.00% - 20.00%
Ni	8.0% - 10.5%
N	0.1% Max

## Mechanical properties

### For round wire

Diameter (mm)	Tolerance (mm)	Tensile strength (N/mm <sup>2</sup> )
0.30 - 0.50	±0.005	
0.51 - 0.70	±0.008	
0.71 - 0.83	±0.009	
0.84 - 1.00	±0.010	
1.01 - 1.60	±0.011	
1.61 - 2.50	±0.014	
2.51 - 4.00	±0.018	
4.01 - 6.30	±0.022	
6.31 - 8.00	±0.028	
0.30 - 0.40		1785 - 2000
0.41 - 0.70		1700 - 1910
0.71 - 1.00		1650 - 1830
1.01 - 1.50		1530 - 1740
1.51 - 2.00		1445 - 1650
2.01 - 2.80		1360 - 1570

Diameter (mm)	Tolerance (mm)	Tensile strength (N/mm <sup>2</sup> )
2.81 - 4.00		1275 - 1490
4.01 - 6.00		1190 - 1400
6.01 - 8.00		1105 - 1320

## Surface conditions

### Surface condition

#### Surface performance

AC-surface 0.30–8.00 mm Ø. The AC-coating can be removed before heat treatment by using a 10–20% nitric acid pickle at room temperature.

## Physical properties

### Heat conductivity

Temperature °C	20	100	200	400
W/(m*°C)	15.0	15.5	17.5	20.0

### Linear expansion

Pro °C	30–100	30–200	30–300
x10 <sup>-6</sup>	17.0	17.5	18.5

## Technical specification

Property	Value	
E modulus of elasticity	Abt. 180 kN/mm <sup>2</sup> in drawn condition.	Abt. 185 kN/mm <sup>2</sup> after heat treatment.
G modulus of shear	Abt. 70 kN/mm <sup>2</sup> in drawn condition.	Abt. 73 kN/mm <sup>2</sup> after heat treatment.
Density	7.90 kg/dm <sup>3</sup>	

## Steel grades and product standards

Nearest equivalent product standards	ASTM A313	BS 2056 304 S15	JIS G4314
Nearest equivalent steel grades	EN/DIN 1.4301	AISI/SAE 304	JIS SUS 304

## Recommendations

### Heat treatment

As soon as possible after coiling, the springs should be stress relieved. Recommended temperature for compression springs or tension springs without initial tension is approx. 350°C for 0.5 – 3 hours.